

Eurofins Umwelt Ost GmbH - Lindenstraße 11 - Gewerbegebiet Freiberg Ost -
D-09627 Bobritzsch-Hilbersdorf

Skånefrö AB
Storgatan 1
27293 Tommarp
SWEDEN

Title : **Analytical Report for Order 12235719**

Test report number : **AR-22-FR-040932-01**

Project name : **ba-se-27-1-3**

Number of samples : **1**

Sample type: **biochar**

Sample Taker: **delivered by client**

Sample reception date : **2022-09-14**

Sample processing time : **2022-09-14 - 2022-10-06**

The test results refer solely to the analysed test specimen. Unless the sampling was done by our laboratory or in our sub-order the responsibility for the correctness of the sampling is disclaimed. This analytical report is only valid with signature and may only be further published completely and unchanged. Extracts or changes require the authorisation of the EUROFINS UMWELT in each individual case.

Our General Terms & Conditions of Sale (GTCS) are applicable, as far as no specific agreements do exist. The GTCS are available on <http://www.eurofins.de/umwelt/avb.aspx>.

Accredited test laboratory according to DIN EN ISO/IEC 17025:2018 DAkkS notification under the DAkkS German Accreditation System for Testing. The laboratory is according (D-PL-14081-01-00) accredited.

Attachments

XML_Export_AR-22-FR-040932-01.xml

Annett Rietschel
Analytical Service Manager
Phone +49 37312076532

Digitally signed 10/6/2022
Annett Rietschel
Prüfleitung



| Parameter | Lab | Accr. | Method | Limit values | | | | | | Description | | sp-se-27-1-3-2 | | |
|-------------------------------------|--------|-------|--|--------------|------------------|----------|-----------|------------------------|---------------------|---------------|-------------------|----------------|-------|--------|
| | | | | EBC-Feed | EBC-Agro Organic | EBC-Agro | EBC-Urban | EBC-Consumer Materials | EBC-Basic Materials | Sample number | | 122131869 | | |
| | | | | | | | | | | LOQ | Unit | ar | db | |
| Biochar properties | | | | | | | | | | | | | | |
| Bulk density < 3 mm | FR | | based on VDLUFA-Methode A 13.2.1 | | | | | | | | kg/m ³ | - | - | 227 |
| specific surface (BET) | SND2/o | | DIN ISO 9277: 2014 | | | | | | | | m ² /g | - | - | 179.92 |
| water holding capacity (WHC) < 2 mm | FR | | DIN EN ISO 14238, A: 2014-03 | | | | | | | | % | - | - | 317.9 |
| Moisture | FR | F5 | DIN 51718: 2002-06 | | | | | | | 0.1 | % (w/w) | - | 25.3 | - |
| Ash content (550°C) | FR | F5 | DIN 51719: 1997-07 | | | | | | | 0.1 | % (w/w) | - | 14.5 | 19.4 |
| Total carbon | FR | F5 | DIN 51732: 2014-07 | | | | | | | 0.2 | % (w/w) | - | 55.2 | 73.9 |
| carbon (organic) | FR | | Calculation | | | | | | | | % (w/w) | - | 55.1 | 73.7 |
| Hydrogen | FR | F5 | DIN 51732: 2014-07 | | | | | | | 0.1 | % (w/w) | - | 1.9 | 2.5 |
| Total nitrogen | FR | F5 | DIN 51732: 2014-07 | | | | | | | 0.05 | % (w/w) | - | 1.93 | 2.59 |
| Sulphur (S), total | FR | F5 | DIN 51724-3: 2012-07 | | | | | | | 0.03 | % (w/w) | - | 0.07 | 0.09 |
| Oxygen | FR | F5 | DIN 51733: 2016-04 | | | | | | | | % (w/w) | - | 1.3 | 1.8 |
| Total inorganic carbon (TIC) | FR | F5 | DIN 51726: 2004-06 | | | | | | | 0.1 | % (w/w) | - | 0.1 | 0.2 |
| carbonate-CO2 | FR | F5 | DIN 51726: 2004-06 | | | | | | | 0.4 | % (w/w) | - | 0.5 | 0.7 |
| H/C ratio (molar) | FR | | Calculation | | | | | | | | | - | 0.40 | 0.40 |
| H/Corg ratio (molar) | FR | | Calculation | < 0.7 | < 0.7 | < 0.7 | < 0.7 | < 0.7 | < 0.7 | | | - | 0.40 | 0.40 |
| O/C ratio (molar) | FR | | Calculation | | | | | | | | | - | 0.018 | 0.018 |
| pH in CaCl2 | FR | | DIN ISO 10390: 2005-12 | | | | | | | | | - | 10.3 | - |
| salt content | FR | | BGK III. C2: 2006-09 | | | | | | | 0.005 | g/kg | - | 12.4 | - |
| salt content | FR | | BGK III. C2: 2006-09 | | | | | | | 0.005 | g/l | - | 2.82 | - |
| Conductivity at 1,2 t pressure | FR | | Internal Method SAA-H-Lf-Pflanzenkohle.040 | | | | | | | 0.01 | mS/cm | - | - | 3.8 |
| Conductivity at 2 t pressure | FR | | Internal Method SAA-H-Lf-Pflanzenkohle.040 | | | | | | | 0.01 | mS/cm | - | - | 5.2 |

| Parameter | Lab | Accr. | Method | Limit values | | | | | | Description | | sp-se-27-1-3-2 | | |
|------------------------------|-----------|-------|--|--------------|------------------|----------|-----------|------------------------|---------------------|---------------|-------------------|----------------|------|------|
| | | | | EBC-Feed | EBC-Agro Organic | EBC-Agro | EBC-Urban | EBC-Consumer Materials | EBC-Basic Materials | Sample number | | 122131869 | | |
| | | | | | | | | | | LOQ | Unit | ar | db | |
| Conductivity at 3 t pressure | FR | | Internal Method SAA-H-Lf-Pflanzenkohle.040 | | | | | | | 0.01 | mS/cm | - | - | 5.9 |
| Conductivity at 4 t pressure | FR | | Internal Method SAA-H-Lf-Pflanzenkohle.040 | | | | | | | 0.01 | mS/cm | - | - | 7.4 |
| Conductivity at 5 t pressure | FR | | Internal Method SAA-H-Lf-Pflanzenkohle.040 | | | | | | | 0.01 | mS/cm | - | - | 7.9 |
| Protein, crude | FR | F5 | VDLUFA Methodenbuch Band III: 2014-09 | | | | | | | | % (w/w) dm | not determined | - | - |
| Fat, crude | FR | F5 | VDLUFA Methodenbuch Band III: 2014-09 | | | | | | | | % (w/w) dm | not determined | - | - |
| Crude fibre | FR | F5 | VDLUFA Methodenbuch Band III: 2014-09 | | | | | | | | % (w/w) dm | not determined | - | - |
| Crude ash | FR | F5 | DIN 51719: 1997-07 | | | | | | | 0.1 | % (w/w) | - | 14.5 | 19.4 |
| HCl-insoluble ash | ES005 A/o | | VDLUFA III 8.2 | | | | | | | | Ma.-% Raw Product | 7.2 | - | - |
| Fluor total (F) | ES005 A/o | WV | VDLUFA III, 17.3.2: 2006 | 150 | | | | | | | mg/kg 88% DM | 18 | - | - |

Polychlorinated dibenzodioxins/-furans (17 PCDD/F) by GC-HRMS

| | | | | | | | | | | | | | | |
|------------------------|-----------|--|------------------------|--|--|--|--|--|--|--|----------|--------|---|---|
| 2,3,7,8-TetraCDD | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | < 0.1 | - | - |
| 1,2,3,7,8-PentaCDD | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | < 0.15 | - | - |
| 1,2,3,4,7,8-HexaCDD | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | < 0.15 | - | - |
| 1,2,3,6,7,8-HexaCDD | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | < 0.15 | - | - |
| 1,2,3,7,8,9-HexaCDD | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | < 0.15 | - | - |
| 1,2,3,4,6,7,8-HeptaCDD | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | 0.26 | - | - |
| OctaCDD | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | 2.4 | - | - |
| 2,3,7,8-TetraCDF | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | < 0.05 | - | - |

| Parameter | Lab | Accr. | Method | Limit values | | | | | | Description | | sp-se-27-1-3-2 | | |
|------------------------------------|--------------|-------|------------------------|--------------|------------------|----------|-----------|------------------------|---------------------|---------------|--------------|----------------|----|---|
| | | | | EBC-Feed | EBC-Agro Organic | EBC-Agro | EBC-Urban | EBC-Consumer Materials | EBC-Basic Materials | Sample number | | ar | db | |
| | | | | | | | | | | 122131869 | | | | |
| | | | | | | | | | | LOQ | Unit | | | |
| 1,2,3,7,8-PentaCDF | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | < 0.01 | - | - |
| 2,3,4,7,8-PentaCDF | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | < 0.01 | - | - |
| 1,2,3,4,7,8-HexaCDF | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | < 0.01 | - | - |
| 1,2,3,6,7,8-HexaCDF | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | < 0.01 | - | - |
| 1,2,3,7,8,9-HexaCDF | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | < 0.01 | - | - |
| 2,3,4,6,7,8-HexaCDF | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | < 0.01 | - | - |
| 1,2,3,4,6,7,8-HeptaCDF | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | < 0.01 | - | - |
| 1,2,3,4,7,8,9-HeptaCDF | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | < 0.01 | - | - |
| OctaCDF | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | < 0.2 | - | - |
| WHO(2005)-PCDD/F TEQ (lower-bound) | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | 0.00331 | - | - |
| WHO(2005)-PCDD/F TEQ (upper-bound) | ES005 A/o | | DIN 38414-S24: 2000-10 | | | | | | | | ng/kg dw | 0.378 | - | - |
| WHO(2005)-PCDD/F TEQ (upper-bound) | ES005 A/o | | calculated | 0.75 | | | | | | | ng/kg 88% DM | 0.333 | - | - |

| Parameter | Lab | Accr. | Method | Limit values | | | | | | Description | | sp-se-27-1-3-2 | | |
|---|--------------|-------|-----------------------|--------------|------------------|----------|-----------|------------------------|---------------------|---------------|--------------|----------------|----|-----------|
| | | | | EBC-Feed | EBC-Agro Organic | EBC-Agro | EBC-Urban | EBC-Consumer Materials | EBC-Basic Materials | Sample number | | ar | db | |
| | | | | | | | | | | LOQ | Unit | | | 122131869 |
| Polychlorinated biphenyl (12 WHO PCB) by GC-HRMS | | | | | | | | | | | | | | |
| PCB 77 | ES005 A/o | | DIN 38407-F3: 1998-07 | | | | | | | | ng/kg dw | 1.2 | - | - |
| PCB 81 | ES005 A/o | | DIN 38407-F3: 1998-07 | | | | | | | | ng/kg dw | < 0.2 | - | - |
| PCB 105 | ES005 A/o | | DIN 38407-F3: 1998-07 | | | | | | | | ng/kg dw | 6.3 | - | - |
| PCB 118 | ES005 A/o | | DIN 38407-F3: 1998-07 | | | | | | | | ng/kg dw | 18 | - | - |
| PCB 114 | ES005 A/o | | DIN 38407-F3: 1998-07 | | | | | | | | ng/kg dw | < 2 | - | - |
| PCB 123 | ES005 A/o | | DIN 38407-F3: 1998-07 | | | | | | | | ng/kg dw | < 2 | - | - |
| PCB 126 | ES005 A/o | | DIN 38407-F3: 1998-07 | | | | | | | | ng/kg dw | < 0.2 | - | - |
| PCB 156 | ES005 A/o | | DIN 38407-F3: 1998-07 | | | | | | | | ng/kg dw | 3.9 | - | - |
| PCB 157 | ES005 A/o | | DIN 38407-F3: 1998-07 | | | | | | | | ng/kg dw | < 2 | - | - |
| PCB 167 | ES005 A/o | | DIN 38407-F3: 1998-07 | | | | | | | | ng/kg dw | 2.2 | - | - |
| PCB 169 | ES005 A/o | | DIN 38407-F3: 1998-07 | | | | | | | | ng/kg dw | < 0.3 | - | - |
| PCB 189 | ES005 A/o | | DIN 38407-F3: 1998-07 | | | | | | | | ng/kg dw | < 3 | - | - |
| WHO(2005)-PCB TEQ (lower-bound) | ES005 A/o | | DIN 38407-F3: 1998-07 | | | | | | | | ng/kg dw | 0.00102 | - | - |
| WHO(2005)-PCB TEQ (upper-bound) | ES005 A/o | | DIN 38407-F3: 1998-07 | | | | | | | | ng/kg dw | 0.0303 | - | - |
| WHO(2005)-PCB TEQ (upper-bound) | ES005 A/o | | calculated | | | | | | | | ng/kg 88% DM | 0.0267 | - | - |
| WHO(2005)-PCDD/F+PCB TEQ (upper-bound) | ES005 A/o | | DIN 38407-F3: 1998-07 | | | | | | | | ng/kg dw | 0.409 | - | - |
| WHO(2005)-PCDD/F+PCB TEQ (upper-bound) | ES005 A/o | | calculated | 1.25 | | | | | | | ng/kg 88% DM | 0.36 | - | - |

| Parameter | Lab | Accr. | Method | Limit values | | | | | | Description | | sp-se-27-1-3-2 | | |
|--|-----------|-------|------------------------|--------------|------------------|----------|-----------|------------------------|---------------------|---------------|--------------|----------------|----|---|
| | | | | EBC-Feed | EBC-Agro Organic | EBC-Agro | EBC-Urban | EBC-Consumer Materials | EBC-Basic Materials | Sample number | | 122131869 | | |
| | | | | | | | | | | LOQ | Unit | ar | db | |
| Polychlorinated biphenyl (7 PCB) by GC-HRMS | | | | | | | | | | | | | | |
| Total 6 Indicator PCB (incl. LOQ) | ES005 A/o | | DIN 38414-S20: 1996-01 | 10 | | | | | | | µg/kg 88% DM | 0.19 | - | - |
| PCB 28 | ES005 A/o | | DIN 38414-S20: 1996-01 | | | | | | | | µg/kg 88% DM | 0.095 | - | - |
| PCB 52 | ES005 A/o | | DIN 38414-S20: 1996-01 | | | | | | | | µg/kg 88% DM | 0.054 | - | - |
| PCB 101 | ES005 A/o | | DIN 38414-S20: 1996-01 | | | | | | | | µg/kg 88% DM | 0.024 | - | - |
| PCB 153 | ES005 A/o | | DIN 38414-S20: 1996-01 | | | | | | | | µg/kg 88% DM | 0.020 | - | - |
| PCB 138 | ES005 A/o | | DIN 38414-S20: 1996-01 | | | | | | | | µg/kg 88% DM | < 0.020 | - | - |
| PCB 180 | ES005 A/o | | DIN 38414-S20: 1996-01 | | | | | | | | µg/kg 88% DM | < 0.020 | - | - |

| Parameter | Lab | Accr. | Method | Limit values | | | | | | Description | | sp-se-27-1-3-2 | | |
|-----------|-----|-------|--------|--------------|------------------|----------|-----------|------------------------|---------------------|---------------|------|----------------|----|--|
| | | | | EBC-Feed | EBC-Agro Organic | EBC-Agro | EBC-Urban | EBC-Consumer Materials | EBC-Basic Materials | Sample number | | 122131869 | | |
| | | | | | | | | | | LOQ | Unit | ar | db | |

Elements from the micro wave pressure digestion acc. to DIN 22022-1: 2014-07

| | | | | | | | | | | | | | | |
|----------------|----|----|-----------------------------------|-----|-----|-----|-----|-----|--|------|-------|---|---|--------|
| Arsenic (As) | FR | F5 | DIN EN ISO 17294-2 (E29): 2017-01 | | 13 | 13 | 13 | 13 | | 0.8 | mg/kg | - | - | < 0.8 |
| Lead (Pb) | FR | F5 | DIN EN ISO 17294-2 (E29): 2017-01 | | 45 | 120 | 120 | 120 | | 2 | mg/kg | - | - | < 2 |
| Cadmium (Cd) | FR | F5 | DIN EN ISO 17294-2 (E29): 2017-01 | | 0.7 | 1.5 | 1.5 | 1.5 | | 0.2 | mg/kg | - | - | < 0.2 |
| Copper (Cu) | FR | F5 | DIN EN ISO 17294-2 (E29): 2017-01 | 70 | 70 | 100 | 100 | 100 | | 1 | mg/kg | - | - | 9 |
| Nickel (Ni) | FR | F5 | DIN EN ISO 17294-2 (E29): 2017-01 | 25 | 25 | 50 | 50 | 50 | | 1 | mg/kg | - | - | 3 |
| Mercury (Hg) | FR | F5 | DIN 22022-4: 2001-02 | | 0.4 | 1 | 1 | 1 | | 0.07 | mg/kg | - | - | < 0.07 |
| Zinc (Zn) | FR | F5 | DIN EN ISO 17294-2 (E29): 2017-01 | 200 | 200 | 400 | 400 | 400 | | 1 | mg/kg | - | - | 155 |
| Chromium (Cr) | FR | F5 | DIN EN ISO 17294-2 (E29): 2017-01 | 70 | 70 | 90 | 90 | 90 | | 1 | mg/kg | - | - | < 1 |
| Boron (B) | FR | F5 | DIN EN ISO 17294-2 (E29): 2017-01 | | | | | | | 1 | mg/kg | - | - | 18 |
| Manganese (Mn) | FR | F5 | DIN EN ISO 17294-2 (E29): 2017-01 | | | | | | | 1 | mg/kg | - | - | 235 |
| Silver (Ag) | FR | F5 | DIN EN ISO 17294-2 (E29): 2017-01 | | | | | | | 5 | mg/kg | - | - | < 5 |

Elements from the pressure digestion acc. to DIN EN 13805: 2014-12

| | | | | | | | | | | | | | | |
|--------------|-----------|----|-----------------------------------|-----|--|--|--|--|--|--|--------------|--------|---|---|
| Arsenic (As) | ES005 A/o | WV | DIN EN ISO 17294-2 (E29): 2017-01 | 2 | | | | | | | mg/kg 88% DM | 0.18 | - | - |
| Lead (Pb) | ES005 A/o | WV | DIN EN ISO 17294-2 (E29): 2017-01 | 10 | | | | | | | mg/kg 88% DM | 1.0 | - | - |
| Cadmium (Cd) | ES005 A/o | WV | DIN EN ISO 17294-2 (E29): 2017-01 | 0.8 | | | | | | | mg/kg 88% DM | 0.029 | - | - |
| Mercury (Hg) | ES005 A/o | WV | DIN EN 15763:2010-04 | 0.1 | | | | | | | mg/kg 88% DM | 0.0053 | - | - |

| Parameter | Lab | Accr. | Method | Limit values | | | | | | Description | | sp-se-27-1-3-2 | | |
|--|-----|-------|---------------------------------|--------------|------------------|----------|-----------|------------------------|---------------------|---------------|---------|----------------|------|------|
| | | | | EBC-Feed | EBC-Agro Organic | EBC-Agro | EBC-Urban | EBC-Consumer Materials | EBC-Basic Materials | Sample number | | 122131869 | | |
| | | | | | | | | | | LOQ | Unit | ar | db | |
| Elements fr. the borate digestion of ash 550 °C acc. to DIN 51729-11:1998-11(AR) | | | | | | | | | | | | | | |
| Calcium as CaO | FR | F5 | DIN EN ISO 11885 (E22): 2009-09 | | | | | | | 0.1 | % (w/w) | - | - | 7.6 |
| Iron as Fe ₂ O ₃ | FR | F5 | DIN EN ISO 11885 (E22): 2009-09 | | | | | | | 0.1 | % (w/w) | - | - | 1.0 |
| Potassium as K ₂ O | FR | F5 | DIN EN ISO 11885 (E22): 2009-09 | | | | | | | 0.1 | % (w/w) | - | - | 15.3 |
| Magnesium as MgO | FR | F5 | DIN EN ISO 11885 (E22): 2009-09 | | | | | | | 0.1 | % (w/w) | - | - | 3.2 |
| Sodium as Na ₂ O | FR | F5 | DIN EN ISO 11885 (E22): 2009-09 | | | | | | | 0.1 | % (w/w) | - | - | 0.5 |
| Phosphorus as P ₂ O ₅ | FR | F5 | DIN EN ISO 11885 (E22): 2009-09 | | | | | | | 0.1 | % (w/w) | - | - | 10.7 |
| sulphur as SO ₃ | FR | F5 | DIN EN ISO 11885 (E22): 2009-09 | | | | | | | 0.1 | % (w/w) | - | - | 0.8 |
| Silicon as SiO ₂ | FR | F5 | DIN EN ISO 11885 (E22): 2009-09 | | | | | | | 0.1 | % (w/w) | - | - | 47.9 |
| Macronutrients | | | | | | | | | | | | | | |
| Total nitrogen | FR | F5 | DIN 51732: 2014-07 | | | | | | | 0.5 | g/kg | - | 19.3 | 25.9 |
| Macronutrients-LiBO₂/Li₂B₄O₇/LiBr-melt of ash 550°C [DIN 51729-11:1998-11] (OS) | | | | | | | | | | | | | | |
| Phosphorus as P ₂ O ₅ | FR | F5 | DIN EN ISO 11885 (E22): 2009-09 | | | | | | | 0.1 | g/kg | - | - | 20.9 |
| Potassium as K ₂ O | FR | F5 | DIN EN ISO 11885 (E22): 2009-09 | | | | | | | 0.1 | g/kg | - | - | 29.7 |
| Calcium as CaO | FR | F5 | DIN EN ISO 11885 (E22): 2009-09 | | | | | | | 0.1 | g/kg | - | - | 14.7 |
| Magnesium as MgO | FR | F5 | DIN EN ISO 11885 (E22): 2009-09 | | | | | | | 0.1 | g/kg | - | - | 6.3 |
| Sodium as Na ₂ O | FR | F5 | DIN EN ISO 11885 (E22): 2009-09 | | | | | | | 0.1 | g/kg | - | - | 0.9 |
| sulphur as SO ₃ | FR | F5 | DIN EN ISO 11885 (E22): 2009-09 | | | | | | | 0.1 | g/kg | - | - | 1.5 |
| Elements fr. the borate digestion of ash 550°C acc. to DIN 51729-11:1998-11(OS) | | | | | | | | | | | | | | |
| Iron (Fe) | FR | F5 | DIN EN ISO 11885 (E22): 2009-09 | | | | | | | 0.1 | g/kg | - | - | 1.3 |
| Silicon (Si) | FR | F5 | DIN EN ISO 11885 (E22): 2009-09 | | | | | | | 0.1 | g/kg | - | - | 43.6 |

| Parameter | Lab | Accr. | Method | Limit values | | | | | | Description | | sp-se-27-1-3-2 | | |
|---|-----|-------|----------------------|--------------|------------------|-----------------|-----------|------------------------|---------------------|---------------|-------|----------------|----|-----------------------|
| | | | | EBC-Feed | EBC-Agro Organic | EBC-Agro | EBC-Urban | EBC-Consumer Materials | EBC-Basic Materials | Sample number | | ar | db | |
| | | | | | | | | | | LOQ | Unit | | | 122131869 |
| Organic contaminants from toluene extraction acc. to EN 16181:2019-08 (method 2) | | | | | | | | | | | | | | |
| Naphthalene | FR | F5 | DIN EN 16181:2019-08 | | | | | | | 0.1 | mg/kg | - | - | 0.8 |
| Acenaphthylene | FR | F5 | DIN EN 16181:2019-08 | | | | | | | 0.1 | mg/kg | - | - | 0.2 |
| Acenaphthene | FR | F5 | DIN EN 16181:2019-08 | | | | | | | 0.1 | mg/kg | - | - | < 0.1 |
| Fluorene | FR | F5 | DIN EN 16181:2019-08 | | | | | | | 0.1 | mg/kg | - | - | 0.1 |
| Phenanthrene | FR | F5 | DIN EN 16181:2019-08 | | | | | | | 0.1 | mg/kg | - | - | 0.3 |
| Anthracene | FR | F5 | DIN EN 16181:2019-08 | | | | | | | 0.1 | mg/kg | - | - | < 0.1 |
| Fluoranthene | FR | F5 | DIN EN 16181:2019-08 | | | | | | | 0.1 | mg/kg | - | - | 0.2 |
| Pyrene | FR | F5 | DIN EN 16181:2019-08 | | | | | | | 0.1 | mg/kg | - | - | 0.2 |
| Benz(a)anthracene | FR | F5 | DIN EN 16181:2019-08 | | | | | | | 0.1 | mg/kg | - | - | < 0.1 |
| Chrysene | FR | F5 | DIN EN 16181:2019-08 | | | | | | | 0.1 | mg/kg | - | - | < 0.1 |
| Benzo(b)fluoranthene | FR | F5 | DIN EN 16181:2019-08 | | | | | | | 0.1 | mg/kg | - | - | < 0.1 |
| Benzo(k)fluoranthene | FR | F5 | DIN EN 16181:2019-08 | | | | | | | 0.1 | mg/kg | - | - | < 0.1 |
| Benzo(a)pyrene | FR | F5 | DIN EN 16181:2019-08 | | | | | | | 0.1 | mg/kg | - | - | < 0.1 |
| Indeno(1,2,3-cd)pyrene | FR | F5 | DIN EN 16181:2019-08 | | | | | | | 0.1 | mg/kg | - | - | < 0.1 |
| Dibenz(a,h)anthracene | FR | F5 | DIN EN 16181:2019-08 | | | | | | | 0.1 | mg/kg | - | - | < 0.1 |
| Benzo(g,h,i)perylene | FR | F5 | DIN EN 16181:2019-08 | | | | | | | 0.1 | mg/kg | - | - | < 0.1 |
| Total 8 EFSA-PAH excl. LOQ | FR | F5 | DIN EN 16181:2019-08 | 1 | 1 | 1 | 1 | 1 | 4 | | mg/kg | - | - | (n. c.) ¹⁾ |
| Total 16 EPA-PAH excl. LOQ | FR | F5 | DIN EN 16181:2019-08 | | 4 ²⁾ | 6 ²⁾ | | | | | mg/kg | - | - | 1.8 |
| Benzo(e)pyrene | FR | F5 | DIN EN 16181:2019-08 | < 1 | < 1 | < 1 | < 1 | < 1 | < 1 | 0.1 | mg/kg | - | - | < 0.1 |
| Benzo-(j)-fluoranthene | FR | F5 | DIN EN 16181:2019-08 | < 1 | < 1 | < 1 | < 1 | < 1 | < 1 | 0.1 | mg/kg | - | - | < 0.1 |

Explanations

LOQ - Limit of quantification

ar - as received

db - dry basis

Lab - Abbreviation of the performing laboratory

Accr. - Abbreviation of the accreditation of the performing laboratory

Comments for results

¹⁾ not calculable

not determined -

These methods apply for animal feed conventional type. The methods are not validated for the matrix biochar and can lead to implausible results.

"Crude protein, crude fiber and crude fat are completely decomposed in the course of complete pyrolysis and are therefore no longer present in biochar. A biochar is considered to be completely pyrolyzed if the H / Corg ratio is < 0.7, which is the prerequisite for EBC certification. Thus, the analysis of crude protein, crude fiber and crude fat is not required and set by definition as 0 g kg⁻¹." [1]

[1] EBC (2012-2022) 'European Biochar Certificate - Guidelines for a Sustainable Production of Biochar.' European Biochar Foundation (EBC), Arbaz, Switzerland. (<http://european-biochar.org>). Version 10.1E from 10th Jan 2022

The parameters identified by ES005A have been performed by the laboratory SGS Analytics Germany GmbH (Jena) (Orlaweg 2, Jena). The accreditation code WV identifies the parameters accredited according to DIN EN ISO/IEC 17025:2018 DAkkS D-PL-14004-10-00 .

The parameters identified by FR have been performed by the laboratory Eurofins Umwelt Ost GmbH (Lindenstraße 11, Gewerbegebiet Freiberg Ost, Bobritzsch-Hilbersdorf). The accreditation code F5 identifies the parameters accredited according to DIN EN ISO/IEC 17025:2018 DAkkS D-PL-14081-01-00 .

The parameters identified by SND2 have been performed by the laboratory Ruhr Lab GmbH (Glückaufstraße 56, Gelsenkirchen).

/o - The analysis has been outsourced.

Explanations regarding Limits

Analysis performed according to guidelines for the sustainable production of biochar - EBC, Version 10.1E - of 10/01/2022.

Ho,V / Hu,p: complies calorific value at constant volume or pressure

AR: related to ash

OS: related to original substance

- 2) The very low PAH limit values only allow an analytical accuracy of 50% for the limit value: "sum 16 EPA-PAH" of 4 mg/kg and of 40% for the limit value of 6 mg/kg which implies an accuracy of ± 2 mg/kg db and ± 2.4 mg/kg db, respectively.

The presentation of comparative values in the analytical report is a service provided by EUROFINS UMWELT. The cited comparative values (limit, guideline or other allocation values) are partially simplified and do not take into account all comments, ancillary provisions and/or exemptions of the corresponding regulations.